




Laboratory Report

Subject : Optical measurements & calculations
Date : 19-05-2011
Author : J.E. Beunk, ing. R.A. Kuipers

Sample: Metallized laminate Cannon Tri-laminates Ltd

Mean NIR reflectance (780-2500 nm)	
Aluminium side	38 %
Black side	2 %



Additional information

Instrument: Perkin Elmer Lambda 900 with 150 mm integrating sphere
Measurement: mean of warp and weft direction measurements